

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. - 56. (Cancelled)

57. (Currently Amended) A plurality of carbon nanosheets on a substrate nanosheet, each of the plurality of carbon nanosheets having a thickness of 2 nanometers or less, wherein the plurality of carbon nanosheets are aligned and stand on their edges roughly vertically to the substrate.

58. (Currently Amended) The plurality of carbon nanosheets nanosheet of claim 57, wherein:

the thickness is 1 nanometer or less; and

each of the plurality of carbon nanosheets nanosheet comprises one to three graphene layers.

59. (Currently Amended) The plurality of carbon nanosheets nanosheet of claim 58, wherein each of the plurality of carbon nanosheets nanosheet comprises a single graphene layer.

60. (Currently Amended) The plurality of carbon nanosheets nanosheet of claim 57, wherein:

the specific surface area of the each of the plurality of carbon nanosheets nanosheet is between 1000 m²/g to 2600 m²/g;

each of the plurality of carbon nanosheets nanosheet has a height between 100 nm and 8 μ m; and

the plurality of carbon nanosheets are nanosheet is in substantially pure form.

the carbon nanosheet is a freestanding nanosheet disposed on its edge on a substrate.

61. (Cancelled)

62. (Currently Amended) A composition comprising a plurality of carbon nanoflake nanoflakes having a specific surface area between $1000 \text{ m}^2/\text{g}$ and $2600 \text{ m}^2/\text{g}$, wherein the carbon nanoflakes are aligned, freestanding and stand on their edges roughly vertically to a substrate.

63. (Currently Amended) The composition of claim 62, wherein each of the plurality of carbon nanoflake has nanoflakes has a thickness of 10 nanometers or less.

64. (Currently Amended) The composition of claim 63, wherein:
each of the plurality of carbon nanoflake has nanoflakes has a thickness of 2 nanometers or less; and
the specific surface area of the each of the plurality of carbon nanoflake has nanoflakes is between $2000 \text{ m}^2/\text{g}$ and $2600 \text{ m}^2/\text{g}$.

65. (Withdrawn – Currently Amended) A method of making carbon nanoflakes comprising forming the nanoflakes on a substrate using RF-PECVD, wherein the carbon nanflakes are aligned, freestanding and stand on their edges roughly vertically to the substrate and have a specific surface area between $1000 \text{ m}^2/\text{g}$ and $2600 \text{ m}^2/\text{g}$.

66. (Withdrawn) The method of claim 65, wherein RF-PECVD is inductively or capacitively coupled.

67. (Withdrawn) The method of claim 65, further comprising:
increasing the substrate temperature during nucleation phase of carbon nanoflake synthesis to form carbon nanosheets comprising a single graphene layer; and
attaching a grounding electrode to the substrate during a nucleation phase of nanoflake formation on the substrate.

68. (Withdrawn) The method of claim 65, wherein:
the substrate temperature is between 550°C and 950°C ;

the PECVD chamber pressure is between 50 mTorr and 200 mTorr; and
PECVD plasma power is equal to or greater than 700 W.

69. (Withdrawn) The method of claim 65, wherein the CVD source gas comprises methane or acetylene, such that the CVD source gas contains a methane to hydrogen ratio between 0.05:99.95 and 100:0, or an acetylene to hydrogen ratio between 0.05:99.95 and 60:40.

70. (Withdrawn – Currently Amended) A method of making carbon nanosheets, comprising:

forming the nanosheets on a substrate, wherein the carbon nanosheets are aligned and stand on their edges roughly vertically to the substrate; and

increasing the substrate temperature during a nucleation phase of carbon nanosheet formation.

71. (Withdrawn) The method of claim 70, wherein inductively or capacitively coupled RF-PECVD is used to form the nanosheets.

72. (Withdrawn) The method of claim 70, further comprising attaching a grounding electrode to the substrate during a nucleation phase of nanoflake formation on the substrate.

73. (Withdrawn) The method of claim 70, wherein:
the substrate temperature is between 550 °C and 950 °C;
the PECVD chamber pressure is between 50 mTorr and 200 mTorr; and
PECVD plasma power is equal to or greater than 700 W.

74. (Withdrawn) The method of claim 70, wherein the CVD source gas comprises methane or acetylene, such that the CVD source gas contains a methane to hydrogen ratio between 0.05:99.95 and 100:0, or an acetylene to hydrogen ratio between 0.05:99.95 and 60:40.

75. (Currently Amended) An article comprising the plurality of carbon nanosheets ~~nanosheet~~ of claim 57, wherein the article is selected from a group consisting of a field emitter, a catalyst support, a hydrogen storage device, a sensor, a blackbody absorber, a composite material, and a coating.

76. (Currently Amended) An article comprising the plurality of carbon nanosheets ~~nanosheet~~ of claim 62, wherein the article is selected from a group consisting of a field emitter, a catalyst support, a hydrogen storage device, a sensor, a blackbody absorber, a composite material, and a coating.

77. - 78. (Cancelled)